



Dassault Falcon Jet Corp  
ATTN: Mr. Halil Cansiz  
Post Office Box 967  
Little Rock, AR 72203

Dear Mr Halil Cansiz:


Project Description: Thirteen (13) coupon sample(s) received on August 31, 2007  
Fabric Protector Corrosivity Test  
P.O. No. L601137

This report is the analytical results and supporting information for the samples submitted to American Interplex Corporation (AIC) on August 31, 2007. The following results are applicable only to the samples identified by the control number referenced above. Accurate assessment of the data requires access to the entire document. Each section of the report has been reviewed and approved by the appropriate laboratory director or a qualified designee.

Materials for this test were supplied to us by Dassault Falcon Jet personnel. The test method has been modified. The test temperature began at 100 C before reaching test method temperature of 38 C. The test was conducted in warm humid air for 7 days to better reflect the corrosive potential of the material.

AMERICAN INTERPLEX CORPORATION

By \_\_\_\_\_

  
John Overbey  
Laboratory Director

Enclosure(s): Analysis Request Form

Dassault Falcon Jet Corp.  
Post Office Box 967  
Little Rock, AR 72203

ANALYTICAL RESULTS

AIC No. 112549-1

Sample Identification: EWO1348-A-1 Synthetic Tap Water

Note: Visual examination revealed slight discoloration without pitting

Analyte	Method	Result	Units	Batch
Corrosion Test	ASTM F1110	See note		C11542

AIC No. 112549-2

Sample Identification: EWO1348-B-1 Synthetic Tap Water

Note: Visual examination revealed slight discoloration without pitting

Analyte	Method	Result	Units	Batch
Corrosion Test	ASTM F1110	See note		C11542

AIC No. 112549-3

Sample Identification: EWO1348-A-2 Synthetic Tap Water

Note: Visual examination revealed slight discoloration without pitting

Analyte	Method	Result	Units	Batch
Corrosion Test	ASTM F1110	See note		C11542

AIC No. 112549-4

Sample Identification: EWO1348-B-2 Synthetic Tap Water

Note: Visual examination revealed slight discoloration without pitting

Analyte	Method	Result	Units	Batch
Corrosion Test	ASTM F1110	See note		C11542

AIC No. 112549-5

Sample Identification: EWO1348-A-3 Synthetic Tap Water

Note: Visual examination revealed slight discoloration without pitting

Analyte	Method	Result	Units	Batch
Corrosion Test	ASTM F1110	See note		C11542

AIC No. 112549-6

Sample Identification: EWO1348-B-3 Synthetic Tap Water

Note: Visual examination revealed slight discoloration without pitting.

Analyte	Method	Result	Units	Batch
Corrosion Test	ASTM F1110	See note		C11542

AIC No. 112549-7

Sample Identification: EWO1348-A-4 COMPASIL F.P.

Note: Visual examination revealed slight discoloration without pitting.

Analyte	Method	Result	Units	Batch
Corrosion Test	ASTM F1110	See note		C11542

Dassault Falcon Jet Corp.  
Post Office Box 967  
Little Rock, AR 72203

ANALYTICAL RESULTS

AIC No. 112549-8

Sample Identification: EWO1348-B-4 COMPASIL F P

Note: Visual examination revealed slight discoloration without pitting.

Analyte	Method	Result	Units	Batch
Corrosion Test	ASTM F1110	See note		C11542

AIC No. 112549-9

Sample Identification: EWO1348-A-5 COMPASIL F P

Note: Visual examination revealed slight discoloration without pitting.

Analyte	Method	Result	Units	Batch
Corrosion Test	ASTM F1110	See note		C11542

AIC No. 112549-10

Sample Identification: EWO1348-B-5 COMPASIL F P

Note: Visual examination revealed slight discoloration without pitting.

Analyte	Method	Result	Units	Batch
Corrosion Test	ASTM F1110	See note		C11542

AIC No. 112549-11

Sample Identification: EWO1348-A-6 COMPASIL F P

Note: Visual examination revealed slight discoloration without pitting.

Analyte	Method	Result	Units	Batch
Corrosion Test	ASTM F1110	See note		C11542

AIC No. 112549-12

Sample Identification: EWO1348-B-6 COMPASIL F P

Note: Visual examination revealed slight discoloration without pitting.

Analyte	Method	Result	Units	Batch
Corrosion Test	ASTM F1110	See note		C11542

AIC No. 112549-13

Sample Identification: EWO1348-A-7 COMPASIL F P

Note: Visual examination revealed slight discoloration without pitting.

Analyte	Method	Result	Units	Batch
Corrosion Test	ASTM F1110	See note		C11542

AIC No. 112549-14

Sample Identification: EWO1348-B-7 COMPASIL F P

Note: Visual examination revealed slight discoloration without pitting.

Analyte	Method	Result	Units	Batch
Corrosion Test	ASTM F1110	See note		C11542

Dassault Falcon Jet Corp.  
Post Office Box 967  
Little Rock, AR 72203

ANALYTICAL RESULTS

AIC No. 112549-15

Sample Identification: EWO1348-A-8 COMPASIL F P

Note: Visual examination revealed slight discoloration without pitting.

Analyte	Method	Result	Units	Batch
Corrosion Test	ASTM F1110	See note		C11542

AIC No. 112549-16

Sample Identification: EWO1348-B-8 COMPASIL F P

Note: Visual examination revealed slight discoloration without pitting.

Analyte	Method	Result	Units	Batch
Corrosion Test	ASTM F1110	See note		C11542

AIC No. 112549-17

Sample Identification: EWO1348-A-9 BLUESTEM F P

Note: Visual examination revealed slight discoloration without pitting.

Analyte	Method	Result	Units	Batch
Corrosion Test	ASTM F1110	See note		C11542

AIC No. 112549-18

Sample Identification: EWO1348-B-9 BLUESTEM F P

Note: Visual examination revealed slight discoloration without pitting.

Analyte	Method	Result	Units	Batch
Corrosion Test	ASTM F1110	See note		C11542

AIC No. 112549-19

Sample Identification: EWO1348-A-10 BLUESTEM F P

Note: Visual examination revealed slight discoloration without pitting.

Analyte	Method	Result	Units	Batch
Corrosion Test	ASTM F1110	See note		C11542

AIC No. 112549-20

Sample Identification: EWO1348-B-10 BLUESTEM F P

Note: Visual examination revealed slight discoloration without pitting.

Analyte	Method	Result	Units	Batch
Corrosion Test	ASTM F1110	See note		C11542

AIC No. 112549-21

Sample Identification: EWO1348-A-11 BLUESTEM F P

Note: Visual examination revealed slight discoloration without pitting.

Analyte	Method	Result	Units	Batch
Corrosion Test	ASTM F1110	See note		C11542

Dassault Falcon Jet Corp.  
Post Office Box 967  
Little Rock, AR 72203

ANALYTICAL RESULTS

AIC No. 112549-22

Sample Identification: EWO1348-B-11 BLUESTEM F.P.

Note: Visual examination revealed slight discoloration without pitting.

Analyte	Method	Result	Units	Batch
Corrosion Test	ASTM F1110	See note		C11542

AIC No. 112549-23

Sample Identification: EWO1348-A-12 BLUESTEM F.P.

Note: Visual examination revealed slight discoloration without pitting.

Analyte	Method	Result	Units	Batch
Corrosion Test	ASTM F1110	See note		C11542

AIC No. 112549-24

Sample Identification: EWO1348-B-12 BLUESTEM F.P.

Note: Visual examination revealed slight discoloration without pitting.

Analyte	Method	Result	Units	Batch
Corrosion Test	ASTM F1110	See note		C11542

AIC No. 112549-25

Sample Identification: EWO1348-A-13 BLUESTEM F.P.

Note: Visual examination revealed slight discoloration without pitting.

Analyte	Method	Result	Units	Batch
Corrosion Test	ASTM F1110	See note		C11542

AIC No. 112549-26

Sample Identification: EWO1348-B-13 BLUESTEM F.P.

Note: Visual examination revealed slight discoloration without pitting.

Analyte	Method	Result	Units	Batch
Corrosion Test	ASTM F1110	See note		C11542